

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) A thermoplastic resin composition which comprises (A) 1 to 99 parts by weight of a polytrimethylene terephthalate and (B) 99 to 1 parts by weight of a polycarbonate, wherein a crystallization enthalpy ΔH_{cc} of component (A), which is obtained when the thermoplastic resin composition is heated from 0°C at 20°C/min, is 0 to 15 J/g, the crystallization enthalpy ΔH_{cc} being calculated according to the following formula (I):

Crystallization peak area ΔH measured using a DSC (J/g) / the content of component (A) based on the total amount of the thermoplastic resin composition (wt%) $\times 100 = \Delta H_{cc}$ (J/g) (I).

2. (Original) The thermoplastic resin composition according to claim 1, wherein a crystallization temperature T_c of the thermoplastic resin composition, which is obtained when the thermoplastic resin composition in a molten state at 270°C is cooled at -20°C/min, is 145°C or more.

3. (Original) The thermoplastic resin composition according to claim 1, wherein a crystallization temperature T_c of the thermoplastic resin composition, which is obtained when the thermoplastic resin composition in a molten state at 270°C is cooled at -20°C/min, is 175°C or more.

4. (Currently Amended) The thermoplastic resin composition according to claim 1 ~~any one of claims 1 to 3~~, wherein the thermoplastic resin composition comprises 1 to 50 parts by weight of component (A) and 99 to 50 parts by weight of component (B).

5. (Currently Amended) The thermoplastic resin composition according to claim 1 ~~any one of claims 1 to 4~~, wherein the thermoplastic resin composition is produced by melt-kneading 2 to 99 parts by weight of a resin composition (D), which comprises 50 to 99 parts by weight of component (A) and 50 to 1 parts by weight of component (B), and 98 to 1 parts by weight of component (B), provided that component (D) + component (B) = 100 parts by weight.

6. (Currently Amended) The thermoplastic resin composition according to claim 1 ~~any one of claims 1 to 4~~, wherein the thermoplastic resin composition further comprises 0.1 to 100 parts by weight of a polyalkylene terephthalate resin (C) based on 100 parts by weight of the component (B),

said polyalkylene terephthalate resin excluding polytrimethylene terephthalate, and

wherein components (A) and (C) have a crystallization enthalpy ΔH_{cc} determined according to, instead of the formula (I), the following formula (II):

Crystallization peak area ΔH measured using a DSC (J/g) /
(Sum of the content of component (A) (wt%) and the content of component (C) (wt%) based on the total amount of the thermoplastic resin composition) $\times 100 = \Delta H_{cc}$ (J/g) (II).

7. (Original) The thermoplastic resin composition according to claim 6, wherein component (C) is a polyethylene terephthalate resin and/or a polybutylene terephthalate resin.

8. (Currently Amended) A resin molded article which is produced by molding the thermoplastic resin composition according to claim 1 ~~any one of claims 1 to 7~~.

9. (Original) The resin molded article according to claim 8, wherein a crystallization enthalpy ΔH_{cc} of component (A) or components (A) and (C), which is obtained when the resin molded article is heated from 0°C at 20°C/min, is 0 to 15 J/g, the crystallization enthalpy ΔH_{cc} being calculated

according to the following formula (III) or (IV):

Crystallization peak area ΔH measured using a DSC (J/g) / the content of component (A) based on the total amount of the resin molded article (wt%) $\times 100 = \Delta H_{cc}$ (J/g) (III), or

Crystallization peak area ΔH measured using a DSC (J/g) / (Sum of the content of component (A) (wt%) and the content of component (C) (wt%) based on the total amount of the resin molded article) $\times 100 = \Delta H_{cc}$ (J/g) (IV).

10. (Original) The resin molded article according to claim 9, wherein a crystallization temperature T_c of the resin molded article, which is obtained when resin molded article in a molten state at 270°C is cooled at - 20°C/min, is 145°C or more.

11. (Original) The resin molded article according to claim 9, wherein a crystallization temperature T_c of the resin molded article, which is obtained when the resin molded article in a molten state at 270°C is cooled at - 20°C/min, is 175°C or more.

12. (Currently Amended) A method for producing the thermoplastic resin composition according to claim 1 ~~any one of claims 1 to 7~~, wherein said method comprises melt-kneading 2 to 99 parts by weight of a resin

composition (D), which comprises 50 to 99 parts by weight of component (A) and 50 to 1 parts by weight of component (B), and 98 to 1 parts by weight of component (B), provided that component (D) + component (B) = 100 parts by weight.

13. (Currently Amended) A method for molding the resin molded article according to claim 8 ~~any one of claims 8 to 11~~, wherein said method comprises dry blending 2 to 99 parts by weight of a resin composition (D), which comprises 50 to 99 parts by weight of component (A) and 50 to 1 parts by weight of component (B), and 98 to 1 parts by weight of component (B), provided that component (D) + component (B) = 100 parts by weight), and subsequently molding and shaping the dry-blended product.